



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



Publication number: **0 313 209 B1**

(12)

## EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: **28.10.92** (51) Int. Cl.<sup>5</sup> **H01S 3/06**

(27) Application number: **88308450.1**

(22) Date of filing: **13.09.88**

Divisional application 92103726.3 filed on  
12/02/92.

(94) **Optical fibre with fluorescent additive.**

(30) Priority: **22.10.87 GB 8724736**

(43) Date of publication of application:  
**26.04.89 Bulletin 89/17**

(45) Publication of the grant of the patent:  
**28.10.92 Bulletin 92/44**

(94) Designated Contracting States:  
**AT BE CH DE ES FR GB GR IT LI LU NL SE**

(56) References cited:  
**FR-A- 2 339 266**  
**GB-A- 2 140 169**  
**US-A- 3 808 549**  
**US-A- 3 894 857**

**APPLIED PHYSICS LETTERS**, vol. 23, no. 7,  
1st October 1973, pages 388-389, American  
Institute of Physics; J. STONE et al.:  
"Neodymium-doped silica lasers in end-  
pumped fiber geometry"

**ELECTRONICS LETTERS**, vol. 23, no. 16, 30th  
July 1987, pages 865-866, Stevenage, Herts,  
GB; C.A. MILLAR et al.: "Low-threshold CW  
operation of an erbium-doped fibre laser  
pumped at 807nm wavelength"

**OPTICAL FIBER COMMUNICATION CONFER-  
ENCE, TECHNICAL DIGEST**, Atlanta, 24th -  
26th February 1986, pages 62-64, paper TUL  
15, IEEE, New York, US; R.J. MEARS et al.:  
"Rare-earth-doped fiber lasers"

(73) Proprietor: **BRITISH TELECOMMUNICATIONS  
public limited company**  
**81 Newgate Street**  
**London EC1A 7AJ(GB)**

(72) Inventor: **Ainslie, Benjamin James**  
**24 Birchwood Drive**  
**Rushmere Ipswich Suffolk IP5 7EB(GB)**  
Inventor: **Craig, Susan Patricia**  
**81 Heath Lane**  
**Ipswich Suffolk IP4 5RX(GB)**  
Inventor: **Armitage, Johnathan Richard**  
**14 Gladstone Road**  
**Ipswich Suffolk IP3 8AT(GB)**

(74) Representative: **Leng, Francis Edward et al**  
**British Telecom Intellectual Property Unit**  
**Room 1304 151 Gower Street**  
**London WC1E 6BA(GB)**

EP 0 313 209 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

## Description

This invention relates to optical fibre with a fluorescent additive and in particular to fibre which is suitable for the construction of fibre lasers.

5 There is currently much technical interest in a wide range of devices in which radiation at wave lengths of 0.3  $\mu\text{m}$  to 4  $\mu\text{m}$  is generated in the core of an optical fibre. In these devices the fibre contains a fluorescent additive which interacts with excitation radiation, usually identified as the "pump radiation", to produce the desired output. The devices take many forms, e.g. broadband sources, super luminescent sources and temperature sensors, but devices which display laser activity are particularly important, especially in telecommunications. It should be realised that telecommunications uses laser activity in two  
10 distinct manners namely optical oscillators and optical amplifiers. However the same doped glass fibres are equally suitable for a plurality of such applications (and often for all such applications).

Stone and Nurus in "Applied Physics Letters" (Volume 23, No. 7, 1 October 1973 at pages 388 and 389) disclose lasers made of neodymium doped silica with end-pumped fibre geometry. One of their  
15 systems has an active core of fused  $\text{SiO}_2$  and  $\text{Nd}_2\text{O}_3$  enclosed in a thin passive sleeve of  $\text{SiO}_2$  and  $\text{Nb}_2\text{O}_5$  and enclosed in a fused jacket of  $\text{SiO}_2$ . The diameter of the active core was about 800 to 150  $\mu\text{m}$  and the length of the samples was 1cm. The function of the thin passive sleeve is to increase the guidance of the core and hence pump efficiency.

US Patent 3 808 549 describes an optical waveguide light source having an active core surrounded by an inner cladding layer and an outer cladding layer. The refractive index of the outer cladding is lower than  
20 the refractive index of the inner cladding which is lower than the refractive index of the core. Pump radiation is launched into the inner cladding layer to which it is confined by the outer cladding. The pump radiation makes many passes through the core whereby its absorption by the core is increased. The signal is generated within the core.

It has long been recognised that the rare earth elements, e.g. Nd, Er, and Yb, display fluorescent properties which make them suitable for use as fluorescent additives in optical fibre. Their fluorescent properties make them particularly suitable for use in the laser devices mentioned above. The operation of a fluorescent device clearly depends on absorption of the pump photons in order to raise ions (or other  
25 fundamental particles) of dopant to an excited state for subsequent emission on a different transition. In a laser device, this emission is stimulated by the presence of a signal photon and, therefore, the operation of a laser device also depends on the interaction of radiation at signal wave length. It is an object of this invention to make efficient use of pump power launched into optical fibre. In the case of optical amplifiers this means achieving high gain for small launched pump powers whereas for optical oscillators it implies a low lasing threshold.

30 Fibre according to the invention has a fluorescent additive unevenly distributed over the cross section of the core and having a higher concentration of the additive at the centre of the core than at the core/cladding boundary. The highest concentrations of additive should ideally be located in those regions of the fibre where, during pumping, the highest intensity of pump radiation is to be expected. Lower or zero concentrations of the additive should be located where only low pump intensities are to be expected.

40 In most pumping schemes the highest intensity of the pump radiation will be located at the centre of the core and it is appropriate to provide the highest dopant concentration at the centre of the core with zero concentration at its periphery. Preferably the core comprises two zones, namely an inner zone surrounded by an outer zone wherein the inner zone contains the dopant and the outer zone contains substantially no dopant. Suitably the inner zone constitutes less than a quarter, e.g. 5 to 15 %, of the cross sectional area of  
45 the core.

The fibre may be implemented in any glass system which is compatible with the fluorescent dopants. Thus, for example, the fibre may be implemented in conventional silicate, phosphate and fluoride systems, eg. fluorides of Zr, Ba, La, Al, Na and Hf or in silica systems, eg.  $\text{SiO}_2$  with additives such as  $\text{GeO}_2$  to adjust the refractive index in the core.

50 In a specific embodiment silica fibre has

(a) a cladding formed of  $\text{SiO}_2$  with  $\text{P}_2\text{O}_5$  to reduce the melting point, and F to offset the increase in refractive index.

(b) an outer core region formed of  $\text{SiO}_2$  with  $\text{GeO}_2$  to increase the refractive index and  $\text{P}_2\text{O}_5$  to reduce the melting point; and

55 (c) an inner core region formed of  $\text{SiO}_2$  with  $\text{Al}_2\text{O}_3$  to increase the refractive index,  $\text{P}_2\text{O}_5$  to decrease the melting point and prevent devitrification and a fluorescent dopant to interact with the pump radiation.

The dimensions of the fibre are preferably such that it is single mode at signal wave length. This implies that it may be able to support several, e.g. up to 4 or 5, modes at pump frequency. The fluorescent

dopants of major interest include the rare earth metals. Of these the most important are Er (which lases by the three level mechanism) and Nd (which lases by the 3 and four level mechanism)

One method of making optical fibre according to the invention utilises the modified chemical vapour deposition process usually identified as MCVD. MCVD is sometimes known as the inside deposition process because the glasses which eventually form the operative parts of the fibre are produced by converting the equivalent chlorides into the desired oxides which are deposited, layer by layer, on the inner surface of a substrate tube. Usually a total of 10 to 30 layers are deposited. As initially deposited the glass is porous but the porous material is immediately fused to give a solid layer upon which subsequent layers are deposited. When all the layers have been deposited the tube is collapsed to a rod which is drawn into fibre.

To make fibre according to the invention this procedure is followed for the cladding and the outer core. The precursor of the inner core is deposited but left in the porous state. Dopants, including the fluorescent additive, are introduced as solution into the porous layer. After solvent removal and conversion to oxides as necessary, the porous layer is consolidated and the tubular configuration is collapsed into a rod which is then drawn into fibre.

It will be appreciated that this, i.e. soaking a solution into a porous layer, is one of many known techniques of introducing dopants into optical fibre. It has been adapted, in accordance with the invention, to provide a small, doped centre region in a larger core. One difficulty inherent in MCVD is that there is a tendency to lose dopant by evaporation from the exposed inner surface. This is not acceptable since the invention requires a high concentration of dopant at the axis. The depleted zone can be removed, e.g. by etching, just before final collapse. Although there appears to be a risk that further losses could occur during the final stage of the collapse, this does not happen to any noticeable extent because:-

(1) The exposed surface is so small that the rate of loss is minimal.

(2) The final stage only takes a time which is too brief for noticeable loss to occur.

However we have most surprisingly discovered that, when aluminium is used to adjust the refractive index of the core, the losses of fluorescent dopant are not noticeable. The aluminium can be introduced at the same time as the fluorescent dopant, e.g. as  $\text{Al}(\text{NO}_3)_3$  in alcoholic solution. During heating the  $\text{Al}(\text{NO}_3)_3$  is converted to  $\text{Al}_2\text{O}_3$ .

The fibre according to the invention can be used to make conventional fibre devices which include a pump for providing excitation radiation for the fluorescent additive.

The invention will now be described by way of example with reference to the accompanying drawing which is a cross section through a fibre according to the invention;

The drawing shows a fibre according to the invention prepared by the MCVD process. This fibre has a residual layer 10 which is the residue of the substrate tube used in the MCVD process. The layer 10 has no optical function. The fibre also has a conventional cladding 11, a core which is generally indicated by the numeral 14, having an (undoped) outer region 12 an inner region 13 which contains a fluorescent dopant, e.g. Er, at a concentration of .001 - 10.0 wt % Er.

Fibre as described above was prepared by a substantially conventional MCVD process in which a substrate tube was rotated in a glass blowing lathe while a reactant gas was passed through its bore. In the course of the preparation three different reactant mixtures, to be specified below, were used.

A short segment of tube, about 2cm long, was heated to reaction temperature by a travelling flame. In this segment chlorides were converted into oxides which deposited as a porous ring downstream of the flame. As the flame traversed, in the case of cladding and outer core, the deposit was fused to form a thin layer on the inner surface of the substrate tube. In the case of inner core, a lower temperature was used so that the deposit did not fuse whereby it remained porous.

The reaction mixture used to form the cladding precursor was obtained by bubbling:-

700ml/min of  $\text{O}_2$  through  $\text{SiCl}_4$ ,

90ml/min of  $\text{O}_2$  through  $\text{POCl}_3$ .

The mixture of these two gas streams was diluted with 1.5 litre/min  $\text{O}_2$  and 1.0 litre/min He. In addition, 6 ml/min of  $\text{CCl}_2\text{F}_2$  were included in the mixture. The maximum temperature in the hot zone was  $1600^\circ\text{C}$  and the flame travelled at 18cm/min.

Five cladding layers were thus deposited on a substrate tube of 10mm inner diameter. These fused together to form a cladding layer of  $\text{SiO}_2$  doped with  $\text{P}_2\text{O}_5$  and fluorine.

(The  $\text{P}_2\text{O}_5$ , which is derived from the  $\text{POCl}_3$ , is incorporated to reduce the melting point of the  $\text{SiO}_2$  which makes the fusion easier. The  $\text{P}_2\text{O}_5$  slightly increases the refractive index of the silica but the fluorine slightly reduces the refractive index. By balancing the two concentrations the refractive index of the five cladding layers is substantially equal to that of pure silica. Thus the  $\text{POCl}_3$  and  $\text{CCl}_2\text{F}_2$  are processing aids which have little or no effect on the performance of the final product which, therefore, consists essentially of

SiO<sub>2</sub>).

Eight layers to form the outer core were deposited next. The reaction mixture used for each layer was obtained by bubbling:-

200 ml/min at O<sub>2</sub> through SiCl<sub>4</sub>

5 200 ml/min of O<sub>2</sub> through GeCl<sub>4</sub>

10 ml/min of O<sub>2</sub> through POCl<sub>3</sub>.

The mixture of these three gas streams was diluted with 1.5 litres/min of O<sub>2</sub>. These eight layers were fused together at 1500°C and the flame travelled at 16 cm/min. This formed the outer core region which consisted essentially of SiO<sub>2</sub> doped with GeO<sub>2</sub> to increase the refractive index and P<sub>2</sub>O<sub>5</sub> to facilitate processing by lowering the melting point of the glass.

10 The precursor at the inner core was deposited in two porous layers. The reaction mixture was obtained by bubbling:-

200 ml/min of O<sub>2</sub> through SiCl<sub>4</sub>

10 ml/min of O<sub>2</sub> through POCl<sub>3</sub>

15 and diluting with 1.5 litres/min of O<sub>2</sub>. The torch traverse rate was 17 cm/min and the maximum temperature was at 1000°C (which is too low to fuse the deposit).

(Note. In all bubbling operations the liquid was at 25°C.) At this point the tube was removed from the lathe and dopants were introduced into the porous layers by immersion for 1 hour in an ethanolic solution of 1M Al(NO<sub>3</sub>)<sub>3</sub>

20 0.08M ErCl<sub>3</sub>.

After soaking, the tube was drained, blown dry with N<sub>2</sub> for one hour, and returned to the lathe where it was heated at about 800°C - 1000°C for a few minutes. This completed solvent evaporation. The temperature was raised to about 1900°C for collapse to a rod. This also ensured conversion of Al(NO<sub>3</sub>)<sub>3</sub> to Al<sub>2</sub>O<sub>3</sub> and ErCl<sub>3</sub> to Er<sub>2</sub>O<sub>3</sub>. The tube was flushed with O<sub>2</sub>/He mixture during all of these stages (about 10 % (volume) of Cl<sub>2</sub> could be introduced into the O<sub>2</sub>/He mix if a very dry product were required.)

25 The resulting preform had a core about 2mm diameter. Analysis (using dispersive X-ray techniques) confirmed that Al and Er<sup>3+</sup> were confined to the central region. The reason for choosing a large core will be briefly explained.

The ultimate objective is a fibre having the dopant, Er<sup>3+</sup>, contained in a very small inner core, e.g. with a diameter of 1 to 3µm. It was decided to achieve this by means of a fat outer core (8 layers), a thin inner core (2 layers) and a high overall draw ratio, i.e. length extension of about 1:10<sup>5</sup>.

The fatness of the preform made it difficult to handle and it was drawn in two stages. First the external diameter was reduced from 7.0mm to 3.2mm, i.e. an axial draw of 1:4.8. The drawn rod was sleeved with a silica tube and then drawn 1: 2.5x10<sup>4</sup> to give the product fibre.

35 (There is a well known problem that dopants are lost during collapse from the inner layers of the preform. This results in a thin axial depletion zone. In the process above described Al<sub>2</sub>O<sub>3</sub> was present and in the presence of this compound no loss of Er<sup>3+</sup> occurred.) The product fibre had the following measurements.

40

45

50

55

Cladding (11)OD 7 $\mu$ mID 4 $\mu$ m

RI matched to silica

Core Outer Region 12OD 4 $\mu$ mID 1.5 $\mu$ mEr<sup>3+</sup> NONECore Inner Region 13Diameter 1.5 $\mu$ mEr<sup>3+</sup> 1 wt %General PropertiesOD 125 $\mu$ mLP<sub>11</sub> Cut Off 790 nm

RI step 0.01

"RI step" denotes the difference between the RI of the core and the RI of the cladding.

A possible theory of the operation of this fibre will now be briefly indicated.

The considerations set out above are particularly pertinent to dopants which lase as a three level system. The three levels are:-

- (a) The ground state,
- (b) the pump level,
- (c) upper laser level, (also known as the metastable level).

The absorption of a pump photon by a ground state ion transfers that ion to the upper pump level from where it decays non-radiatively to the upper laser level. That ion can then return to the ground state via the lasing transition, i.e. gives out a signal photon. In order to achieve the population inversion essential for laser operation it is necessary to pump more than half the dopant ions from the ground state to the upper laser level. Thus it is important to note that, at a particular point in space, if fewer than half the ions have been pumped to the upper laser level then the signal beam will be attenuated at that point.

It is therefore extremely desirable to preferentially locate the fluorescence additive where the pump intensity is highest, i.e. on the axis and to prevent there being any dopant ions in the regions where the pump intensity is lower.

The signal beam, which being single mode also has its maximum intensity on the axis, overlaps well with the excited dopant ions and thus effectively depopulates the upper laser level.

In order to illustrate the benefit of the invention comparative measurements were made on two very similar fibres both of which used Er<sup>3+</sup> ions as the fluorescent species. The fibre, identified as "A", had the Er<sup>3+</sup> ions located in a centre core Region 13 as shown in Figure 1. The comparative fibre, identified as "X", had the more standard Er<sup>3+</sup> distribution, i.e. uniformly distributed over the whole of the core. Details of both fibres are given in Table 1.

Diameters ( $\mu\text{m}$ )	A	X
Total	125	125
To Cladding (11)	6.0	6.0
To Core (12)	3.5	3.5
Inner Region (13)	1.0	NONE
Ri Step	0.0100 $\pm$ 0.005	0.0095 $\pm$ 0.005
LP <sub>11</sub> Mode cut off (nm)	790	790

In the case of fibre A the dopant was contained only in the inner region 13. Based on this region alone the concentration of  $\text{Er}^{3+}$  was 0.45% wt or 0.037% wt based on the total core 14. For fibre X the concentration of  $\text{Er}^{3+}$  was 0.05% wt based on the total core 14.

The performances of the two fibres were compared by measuring the "transparency power" of each.

To measure the transparency power a short length of fibre is used so that pump power does not change significantly along the length. The test comprises launching the signal at wave length 1.54  $\mu\text{m}$  and pump at wave length 528.7nm into the opposite ends of the fibre. The input and output powers of the signal are measured for several values of pump power. There exists a specific pump power at which the signal is neither amplified or attenuated and this power is known as the "transparency power". This name is considered appropriate because, at this pump power, the fibre simulates a perfectly transparent window. At higher pump powers than the transparency power, the fibre amplifies the signal beam whereas at lower pump powers the fibre attenuates the signal beam. The transparency power is a direct measure of the performance of the invention and the lower the transparency power the better the performance. The transparency powers of the two fibres was

Fibre A	0.8mW
Fibre X	1.4mW
Ratio	1 : 1.75

Thus the fibre according to the invention gave gain at much lower pump power than the comparative fibre.

#### Claims

1. An optical fibre, suitable for forming fluorescent devices, which contains a fluorescent dopant in its core, characterised in that the concentration of the dopant is greater on the core axis than at the interface between the core and the cladding.
2. A fibre according to Claim 1 wherein the core comprises an inner region and an outer region surrounding the inner region wherein substantially all of the dopant is contained in the inner region.
3. A fibre according to claim 2, wherein the inner region constitutes not more than a quarter of the total cross sectional area of the core.
4. A fibre according to claim 3, wherein the inner region constitutes 5% to 15% of the cross sectional area of the core.
5. A fibre according to any one of claims 2 to 4, wherein both core regions contain  $\text{SiO}_2$  and the mole ratio of Si to dopant in the inner core region is between  $1:10^{-4}$  and 1:10.
6. A fibre according to any one of claims 2-5, wherein the dopant is substantially uniformly distributed in the inner region of the core.
7. A fibre according to any one of the preceding claims which is monomode at signal wave length.
8. A fibre according to any one of the preceding claims wherein the dopant is capable of lasing transition.
9. A fibre according to Claim 8, wherein the dopant is a three level lasing element.

10. A fibre according to any one of the preceding claims, wherein the dopant is a rare earth element.
11. A fibre according to claim 10, wherein the dopant is selected from Er, Nd, Pr, Ho, Yb and Tm.
- 5 12. A fibre according to claim 11, wherein the dopant is  $\text{Er}^{3+}$ .
13. An optical fibre which comprises
  - (a) a cladding region formed of a first glass composition having a first refractive index;
  - (b) an outer core region surrounded by said cladding region and formed of a second glass composition having a second refractive index said second refractive index being higher than said first refractive index;
  - (c) an inner core region surrounded by said outer core region and formed of a third glass composition having a refractive index substantially equal to said second refractive index wherein said third glass composition contains a dopant which provides an element selected from Er, Nd, Pr, Ho, Yb and Tm in a form capable of undergoing lasing transitions wherein the concentration of said dopant is such as to provide about 1 to 10% by weight of said element based on the total third glass composition.
14. An optical fibre according to claim 13, wherein the concentration of the dopant is 0.1 to 10% by weight.
15. An optical fibre according to any one of the preceding claims, wherein the cladding region consists essentially of  $\text{SiO}_2$ , the outer core region consists essentially of  $\text{SiO}_2$  and  $\text{GeO}_2$  and the inner core region consists essentially of  $\text{SiO}_2$ ,  $\text{GeO}_2$  and the lasing dopant.

#### 25 Patentansprüche

1. Optische Faser, die geeignet ist zum Bilden fluoreszierender Vorrichtungen, welche eine fluoreszierende Dotierung in ihrem Kern enthält, dadurch gekennzeichnet, daß die Konzentration der Dotierung auf der Kernachse größer ist als an der Grenzfläche zwischen dem Kern und der Plattierung.
2. Faser nach Anspruch 1, wobei der Kern einen inneren Bereich und einen den inneren Bereich umgebenden äußeren Bereich aufweist, wobei im wesentlichen die gesamte Dotierung in dem inneren Bereich enthalten ist.
3. Faser nach Anspruch 2, wobei der innere Bereich nicht mehr als ein Viertel der gesamten Querschnittsfläche des Kerns bildet.
4. Faser nach Anspruch 3, wobei der innere Bereich 5 % bis 15 % der Querschnittsfläche des Kerns darstellt.
5. Faser nach einem der Ansprüche 2 bis 4, wobei beide Kernbereiche  $\text{SiO}_2$  enthalten und das Molverhältnis von Si zur Dotierung in dem inneren Kernbereich zwischen  $1:10^{-4}$  und  $1:10$  liegt.
6. Faser nach einem der Ansprüche 2 bis 5, wobei die Dotierung im wesentlichen gleichförmig in dem inneren Bereich des Kerns verteilt ist.
7. Faser nach einem der vorhergehenden Ansprüche, die bei einer Signalwellenlänge eine Monomodenfaser ist.
8. Faser nach einem der vorhergehenden Ansprüche, wobei die Dotierung zu einem Laserübergang in der Lage ist.
9. Faser nach Anspruch 8, wobei die Dotierung ein 3-Niveau-Laserelement ist.
10. Faser nach einem der vorhergehenden Ansprüche, wobei die Dotierung ein Element der Seltenen Erden ist.
11. Faser nach Anspruch 10, wobei die Dotierung aus Er, Nd, Pr, Ho, Yb und Tm ausgewählt ist.

12. Faser nach Anspruch 11, wobei die Dotierung  $\text{Er}^{3+}$  ist.
13. Optische Faser, welche aufweist:
- (a) einen Plattierungsbereich, der aus einer ersten Glaszusammensetzung mit einem ersten Brechungsindex gebildet wird.
  - (b) einen durch den Plattierungsbereich umgebenen äußeren Kernbereich, der aus einer zweiten Glaszusammensetzung gebildet ist mit einem zweiten Brechungsindex, wobei der zweite Brechungsindex höher ist als der erste Brechungsindex;
  - (c) einen durch den äußeren Kernbereich umgebenen inneren Kernbereich, der aus einer dritten Glaszusammensetzung gebildet ist mit einem Brechungsindex, der im wesentlichen gleich dem zweiten Brechungsindex ist, wobei die dritte Glaszusammensetzung eine Dotierung enthält, die ein Element bereitstellt, welches aus Er, Nd, Pr, Ho, Yb und Tm in einer Form ausgewählt wird, die in der Lage ist, sich Laserübergängen zu unterziehen, wobei die Konzentration der Dotierung derart ist, daß 0,001 bis 10 Gewichtsprozent Element bezogen auf die gesamte Glaszusammensetzung bereitgestellt ist.
14. Optische Faser nach Anspruch 13, wobei die Konzentration der Dotierung 0,1 bis 10 Gewichtsprozent ist.
15. Optische Faser nach einem der vorhergehenden Ansprüche, wobei der Plattierungsbereich im wesentlichen aus  $\text{SiO}_2$  besteht, der äußere Kernbereich im wesentlichen aus  $\text{SiO}_2$  und  $\text{GeO}_2$  besteht und der innere Kernbereich im wesentlichen aus  $\text{SiO}_2$ ,  $\text{GeO}_2$  und der Laserdotierung besteht.

#### Revendications

1. Une fibre optique, apte à former des dispositifs fluorescents, qui contient dans son noyau un dopant fluorescent, caractérisée en ce que la concentration de dopant est plus grande sur l'axe du noyau qu'à l'interface entre le noyau et la gaine.
2. Une fibre selon la revendication 1 dans laquelle le noyau comprend une zone intérieure et une zone extérieure, entourant la zone intérieure, dans laquelle sensiblement tout le dopant est contenu dans la zone intérieure.
3. Une fibre selon la revendication 2, dans laquelle la zone intérieure ne constitue pas plus d'un quart de la surface totale d'une coupe transversale du noyau.
4. Une fibre selon la revendication 3, dans laquelle la zone intérieure constitue de 5 % à 15 % de la surface d'une coupe transversale du noyau.
5. Une fibre selon l'une quelconque des revendications 2 à 4, dans laquelle les deux zones de noyau contiennent du  $\text{SiO}_2$  et le rapport molaire entre Si et le dopant dans la zone intérieure de noyau est compris entre  $1:10^{-4}$  et 1:10.
6. Une fibre selon l'une quelconque des revendications 2 à 5, dans laquelle le dopant est réparti de façon sensiblement uniforme dans la zone intérieure du noyau.
7. Une fibre selon l'une quelconque des revendications précédentes qui est monomode à la longueur d'onde de signal.
8. Une fibre selon l'une quelconque des revendications précédentes dans laquelle le dopant est susceptible d'une transition à effet laser.
9. Une fibre selon la revendication 8, dans laquelle le dopant est un élément à effet laser à trois niveaux.
10. Une fibre selon l'une quelconque des revendications précédentes, dans laquelle le dopant est un élément des terres rares.
11. Une fibre selon la revendication 10, dans laquelle le dopant est choisi parmi Er, Nd, Pr, Ho, Yb et Tm.



12. Une fibre selon la revendication 11, dans laquelle le dopant est  $\text{Er}^{3+}$ .
13. Une fibre optique qui comprend :
  - (a) une zone de gaine formée d'une première composition de verre à premier indice de réfraction;
  - (b) une zone extérieure de noyau entourée par ladite zone de gaine et formée d'une deuxième composition de verre à deuxième indice de réfraction, ledit deuxième indice de réfraction étant supérieur audit premier indice de réfraction;
  - (c) une zone intérieure de noyau entourée par ladite zone extérieure de noyau et formée d'une troisième composition de verre à indice de réfraction sensiblement égal audit deuxième indice de réfraction, dans laquelle ladite troisième composition de verre contient un dopant qui inclut un élément choisi parmi Er, Nd, Pr, Ho, Yb et Tm sous une forme susceptible d'être soumise à des transitions d'effet laser et dans laquelle la concentration dudit dopant est apte à constituer 0,001 à 10 % en poids dudit élément, sur la base du poids total de la troisième composition de verre.
14. Une fibre optique selon la revendication 13, dans laquelle la concentration du dopant est comprise entre 0,1 et 10 % en poids.
15. Une fibre optique selon l'une quelconque des revendications précédentes, dans laquelle la zone de gaine consiste essentiellement en  $\text{SiO}_2$ , la zone extérieure de noyau consiste essentiellement en  $\text{SiO}_2$  et  $\text{GeO}_2$  et la zone intérieure de noyau consiste essentiellement en  $\text{SiO}_2$ ,  $\text{GeO}_2$  et le dopant à effet laser.

